

HIGH PERFORMANCE ACOUSTIC CEILING TILE





Mid range absorption



Hygrothermal



Fire Test Group-1S



High Attenuation



Glasswool



Mineral Fibre

FEATURES

- Phonic Harmony + is a composite tile with a refined white painted, monolithic, pre-finished face.
- It has an absorptive layer with an attenuating backer behind.
- The absorbent face is made from a high density glass- wool.
- For Green Star rated projects, Phonic meets the Greenguard Emission Certificate standard.

V1.0 11/23









Phonic Harmony+

Sound absorption	Thickness 23 mm	HZ	125 0.55	250 0.45	500 0.55	1000 0.85	2000 1.00	4000 1.00	α _w 0.65	NRC 0.75	
		αр									
	*Tested to AS/ISO 354: 2006 Acoustics-Measurement of sound absorption in a reverberation room . α_W , calculated to ISO 11654 1997, NRC calculated to ASTM C423. Air gap type E-400.										
Ceiling attenuation coefficient	Thickness 23 mm			CAC 39							
	*Tested to ASTM E1414-11A Standard test method for airborne sound attenuation between rooms sharing a common ceiling plenum.										
Fire test	Thickness			Class							
	20 mm			Group 1-S							
	*Tested to ISO 5660.1-2015 Reaction to fire tests – Heat release smoke production and mass loss rate part 1 (cone calorimeter). NZBC C/VM2 Apprendix A.										
Sizes	Thickness			1200 x 600 mm, 600 x 600 mm (other sizes							
	23 mm				ole on in						
Weight	3.292 kg/m ²										
Density	100 kg/m³ (glasswool), 250 kg/m³ (mineral fibre)										
Edge details	Square edge, reveal edge										
Light reflectance	87%										
	*Tested to ASTM E1477-98 standa	ard test n	nethod								
Colour	White, Black										
Thermal resistance	0.4 m ² k/w (calculated)										
Sustainability	Recycled product: the rate of pre-consumer recycled content in Phonic fibreglass ceiling tiles										
	is 80%. The recycled content includes 30% industrial waste and 70% civilian used waste, all										
	procured from reclamation de	oots.									
VOC	*Tested to ASTM D519-06 standard test method										
Warranty	30 Year product warranty when installed in accordance with NZ1170.5										
NZ Building Code	Exceeds clause B2 - durability, 5 years										

^{*}Test reports available upon request











V2.0 06/25